


6165 W Detroit St. • Chandler AZ 85226  
 +1 (602) 276-0406 • +1 (800) 528-8242 • FAX +1 (480) 961-0513  
 www.crafco.com

**READ BEFORE USING THIS PRODUCT**

**GENERAL** Crafcro PolyFlex Type 2 sealant is a hot-applied, asphalt based product used to fill cracks and joints in asphalt or Portland cement concrete pavements in moderate to hot climates. PolyFlex Type 2 is supplied in solid form which when melted and properly applied forms a highly adhesive and flexible compound that resists cracking in the winter and resists flow at summer temperatures. PolyFlex Type 2 is used in highway, street, airfield and parking lot pavements and is applied to pavement cracks using pressure feed melter applicators. At application temperature PolyFlex Type 2 is a medium viscosity product which flows and penetrates cracks. PolyFlex Type 2 is formulated as an economical yet effective pavement maintenance crack filling product. Compared to products based on reclaimed rubber, PolyFlex Type 2 offers lower viscosity for easier application, improved summer temperature pick-up resistance, quicker set times, and improved low temperature flexibility. Polyflex Type 2 has been a quality Crafcro product for over 25 years. Several states have developed specifications based on performance of PolyFlex Type 2. VOC = 0 g/l.

**USAGE GUIDELINES** PolyFlex Type 2 is applicable for Filler/Overband Use in moderate to hot climates with high and low pavement temperatures identified in the chart. Pavement temperatures for the project location are determined using FHWA LTPPBIND V 3.1 and sealant or filler use is determined following Crafcro Product Selection Procedures.

 Applicable Pavement Temperatures



**SPECIFICATION CONFORMANCE** The Crafcro recommended specification limits for PolyFlex Type 2 when heated in accordance with ASTM D5078 to the maximum heating temperature are as follows:

<b>Test</b>	<b>Specification Limits</b>
Cone Penetration (ASTM D5329)	35-55
Resilience (ASTM D5329)	40% min.
Softening Point (ASTM D36)	200 °F (93 °C) min
Ductility 77 °F (25 °C) (ASTM D113)	30cm min
Flexibility, 1/8" (3.2 mm) specimen, 90° bend, 10 sec., 1" (25 mm) mandrel (ASTM D3111 Modified)	Pass at 20 °F (-7 °C)
Flow, 140 °F (60 °C), 5 h, (ASTM D5329)	3 mm max.
Viscosity, 400 °F (204 °C) (ASTM D2669)	100 Poise max.
Asphalt Compatibility (ASTM D5329)	Pass
Bitumen Content (ASTM D4)	60% min.
Tensile Adhesion, 1" (25.4mm) thickness (ASTM D5329)	500% min.
Maximum Heating Temperature	400 °F (204 °C)
Minimum Application Temperature	380 °F (193 °C)

**INSTALLATION** The unit weight of Crafcro PolyFlex Type 2 sealant is 10.5 lbs. per gallon (1.26kg/L) at 60 °F (15.5 °C). Prior to use, the user must read and follow Installation Instructions for Hot-Applied RoadSaver, PolyFlex and Asphalt Rubber Products to verify proper product selection, heating methods, pavement preparation procedures, application geometry, usage precautions and safety procedures. These instructions are provided with each pallet of product.

**PACKAGING** Product is supplied in either cardboard boxes, or in meltable, boxless PLEXI-melt packaging. Both package types are labeled in accordance with OSHA, GHS, and specification requirements; are sold by net weight; are interlock stacked on 48 x 40 in. (122 x 102 cm) 4-way pallets; can be stored outside; and are covered with a weather resistant pallet cover and 2 layers of UV protected stretch wrap.

- o **BOX** packaging consists of cardboard boxes containing approximately 30 lb. (13.6 kg) of product with 75 boxes per pallet, weighing approximately 2250 lb. (1020 kg). Boxes contain a quick melting release film for easy removal and are taped closed, without any staples.
- o **PLEXI-melt** packaging consists of 30 lb. (13.6 kg) blocks of product with 70 packages per pallet, weighing 2100 lb. (952 kg). To use, the pallet wrap is removed, and individual blocks are placed in the melter. There are no cardboard boxes or other cardboard components to open, empty, handle, or dispose of. PLEXI-melt packaging quickly melts into the product without affecting specification conformance.

**WARRANTY** CRAFCO, Inc. warrants that CRAFCO products meet applicable ASTM, AASHTO, Federal or State specifications at time of shipment. Techniques used for the preparation of the cracks and joints prior to sealing or filling are beyond our control as are the use and application of the products; therefore, Crafcro shall not be responsible for improperly applied or misused products. Remedies against Crafcro, Inc., as agreed to by Crafcro, are limited to replacing nonconforming product or refund (full or partial) of purchase price from Crafcro, Inc. All claims for breach of this warranty must be made within three (3) months of the date of use or twelve (12) months from the date of delivery by Crafcro, Inc. whichever is earlier. There shall be no other warranties expressed or implied. **For optimum performance, follow Crafcro recommendations for product installation.**